



**TESTING SERVICES, INC.**  
 817 SHOWALTER AVE. • P.O. BOX 2041  
 DALTON, GEORGIA 30722-2041  
 PHONE: (706) 226-1400 • FAX: (706) 226-6118



## TEST REPORT

<b>CLIENT:</b>	Flooring Liquidators	<b>REPORT NUMBER:</b>	64009E
	736 Mariposa Road, Suite F	<b>LAB TEST NUMBER:</b>	2710-3528
	Modesto, CA 95354	<b>DATE:</b>	June 5, 2015
		<b>PAGE:</b>	1 of 1

**Test Material:**

<b>Turf Identification</b>	Tough Turf
<b>Infill System</b>	2.5 lbs/ft <sup>2</sup> 20/40 Silica Sand
<b>Sub Base</b>	2.0" Aggregate Rock

**INTRODUCTION:** Testing Services Inc was instructed by the client, to perform ADA wheelchair accessibility for the above described material being used under and around playground equipment.

**TEST METHOD:** *ASTM F1951: Standard Specification for Determination of Accessibility of Surface Systems Under and Around Playground Equipment*

**REQUIREMENT:** A surface in place shall have average work per foot (work per meter) values for straight propulsion and for turning *less* than the average work per foot (work per meter) values for straight propulsion and for turning, respectively, on a hard, smooth, surface with a grade of 1:14 (7.1 %).

**PROCEDURE:** **Test Surface Preparation:** Tests were conducted on 5/29/15 indoors at TSi Laboratories in an environment of 75°F and 62% R.H. The synthetic turf was installed over the above identified sub-base and infilled with the above identified infill in a wooden box (44"W x 117"L). The system, prior to testing, was slightly compacted using a water-filled lawn roller to simulate foot traffic.

**Wheelchair/Operator:** The wheelchair used in these tests was manufactured by *Invcare*, Model Action Xtra, serial Number 98J84142. This wheelchair is totally adjustable, a necessity for these tests. The pneumatic tires were inflated to 60 psi on the rear and 32 psi on the front. The weight of the wheelchair was 24.25 pounds and the operator's weight was 165 pounds for a total of 189 pounds. The operator's distribution was adjusted to 60% on the rear wheels and 40 % on the front.

**Torque Measuring System:** A certified *Dillion Electronic Force Gauge*, Model BFG 500N, S/N 98-2277-07 was used as an interface between a *Dell* Laptop and a certified *Dillion Smart Torque Wrench*, S/N 97-0085-01. Software, also from Dillon, logged the load vs. time and integrated the area under the resulting curves. The adapters and accessories needed to attach the instrumentation were fabricated locally. This total package added 10 pounds to the total weight bringing the total to 199 pounds.

**TEST RESULTS:** (Average Work/ft-Force)

<b>Baseline Straight</b>	<b>Tough Turf with above listed infill over 2" Aggregate Rock</b>
14.33 lbs	11.97 lbs
<b>Baseline Turning</b>	<b>Tough Turf with above listed infill over 2" Aggregate Rock</b>
10.14 lbs	8.18 lbs

**CONCLUSION:** The above listed material *meets/exceeds* both the straight line and turning propulsion requirements set forth in this test method and therefore, passes the standard.

Approved By:

Erle Miles, Jr V.P., Testing Services Inc

TSi Accreditation: Our laboratory is accredited with US Dept of Commerce, National Institute of Standards and Technology: ISO/IEC 17025:2005. Testing Services, Inc is a certified independent laboratory by the Synthetic Turf Council